

DuPont™ Crastin® PBT

thermoplastic polyester resin

Crastin® 6129C NC010

Crastin® 6129C NC010 is an unreinforced, high viscosity polybutylene terephthalate resin for extrusion and injection molding.

Property	Test Method	Units	Value
Identification			
Resin Identification	ISO 1043		PBT
Part Marking Code	ISO 11469		>PBT<
Mechanical			
Yield Stress	ISO 527	MPa (kpsi)	58 (8.4)
Strain at Break	ISO 527	%	
50mm/min			200
Nominal Strain at Break	ISO 527	%	>50
Yield Strain	ISO 527	%	5
Tensile Modulus	ISO 527	MPa (kpsi)	2600 (377)
Tensile Creep Modulus	ISO 899	MPa (kpsi)	
1h			2600 (377)
1000h			1800 (261)
Flexural Modulus	ISO 178	MPa (kpsi)	2350 (340)
Flexural Strength	ISO 178	MPa (kpsi)	85 (12.3)
Notched Charpy Impact Strength	ISO 179/1eA	kJ/m ²	
-30°C (-22°F)			4
23°C (73°F)			5.5
Unnotched Charpy Impact Strength	ISO 179/1eU	kJ/m ²	
-30°C (-22°F)			NB
23°C (73°F)			NB

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
 Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Crastin® are trademarks or registered trademarks of DuPont Company. Copyright© 2005.

050424/050422

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-50102.

Crastin® 6129C NC010

Property	Test Method	Units	Value
Thermal			
Deflection Temperature 0.45MPa	ISO 75f	°C (°F)	115 (239)
0.45MPa, Annealed			180 (356)
1.80MPa			50 (122)
1.80MPa, Annealed			60 (140)
Melting Temperature 10°C/min	ISO 11357-1/-3	°C (°F)	225 (437)
CLTE, Normal	ISO 11359-1/-2	E-4/C (E-4/F)	
-40 - 23°C (-40 - 73°F)			0.9 (0.5)
23 - 55°C (73 - 130°F)			1.3 (0.72)
55 - 160°C (130 - 320°F)			1.62 (0.9)
CLTE, Parallel	ISO 11359-1/-2	E-4/C (E-4/F)	
-40 - 23°C (-40 - 73°F)			0.72 (0.4)
23 - 55°C (73 - 130°F)			1.3 (0.72)
55 - 160°C (130 - 320°F)			1.8 (1.0)
Thermal Conductivity	DIN 51046	W/m K (Btu in/h ft ² F)	0.25 (1.7)
Vicat Softening Temperature	ISO 306	°C (°F)	
10N, 50°C/h			215 (420)
50N, 50°C/h			175 (350)
Hot Ball Pressure Test Plate 3mm	VDE 0470	°C (°F)	180 (356)
Electrical			
Surface Resistivity	IEC 60093	ohm	>1E12
Relative Permittivity	IEC 60250		
1E6 Hz			3.2
50Hz			3.8

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
 Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Crastin® are trademarks or registered trademarks of DuPont Company. Copyright© 2

050424/050422

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-50102.

Crastin® 6129C NC010

Property	Test Method	Units	Value
Electrical			
Volume Resistivity	IEC 60093	ohm m	>1E13
Dissipation Factor	IEC 60250	E-4	
1E6 Hz			200
50Hz			20
Electric Strength	IEC 60243-1	kV/mm (V/mil)	
1.0mm			26 (660)
2.0mm			15 (380)
Electrolytical Corrosion	IEC 60426		
4.0mm			A1
CTI	UL 746A	V	>600
Flammability			
Flammability Classification	IEC 60695-11-10		
0.92mm			HB
Flammability Classification	UL94		
0.92mm			HB
Oxygen Index	ISO 4589-1/-2	%	22
Glow Wire Flammability Index	IEC 60695-2-12	°C	
0.92mm			925
1.5mm			960
3.0mm			850
Glow Wire Ignition Temperature	IEC 60695-2-13	°C	
0.92mm			825
1.5mm			825
3.0mm			825
High Amperage Arc Ignition Resistance	UL 746A	arcs	
0.92mm			120
Hot Wire Ignition	UL 746A	s	
0.92mm			7
1.5mm			15
3.0mm			30

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
 Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Crastin® are trademarks or registered trademarks of DuPont Company. Copyright© 2

050424/050422

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-50102.

Crastin® 6129C NC010

Property	Test Method	Units	Value
Temperature Index			
RTI, Electrical 0.92mm	UL 746B	°C	75
RTI, Impact 0.92mm	UL 746B	°C	75
RTI, Strength 0.92mm	UL 746B	°C	75
Other			
Density	ISO 1183	kg/m ³ (g/cm ³)	1300 (1.30)
Ball Indentation Hardness H 358/30	ISO 2039-1	MPa (kpsi)	139 (20)
Water Absorption Equilibrium 50%RH Saturation, immersed	ISO 62, Similar to	%	0.2 0.4
Molding Shrinkage Normal, 2.0mm Parallel, 2.0mm	ISO 294-4	%	1.5 1.7
Processing			
Melt Temperature Range		°C (°F)	240-260 (465-500)
Melt Temperature Optimum		°C (°F)	250 (480)
Mold Temperature Range		°C (°F)	30-130 (85-265)
Mold Temperature Optimum		°C (°F)	80 (175)
Drying Time, Dehumidified Dryer		h	2-4
Drying Temperature		°C (°F)	110-130 (230-265)
Processing Moisture Content		%	<0.04
Snake Flow		mm	
90MPa, 5x0.30mm			8
90MPa, 5x0.50mm			26
90MPa, 5x0.75mm			60
90MPa, 5x1.00mm			95

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
 Test temperatures are 23°C unless otherwise stated.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Crastin® are trademarks or registered trademarks of DuPont Company. Copyright© 2

050424/050422

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement", H-50102.