

DuPont™ Crastin® PBT

thermoplastic polyester resin

PRELIMINARY DATA

Crastin® SK612SF NC010

Crastin® SK612SF is a 15% glass fiber reinforced, low viscosity polybutylene terephthalate for injection molding. It has high flow characteristics and is specifically suitable for super fast production.

Property	Test Method	Units	Value
Identification			
Resin Identification	ISO 1043		PBT-GF15
Part Marking Code	ISO 11469		>PBT-GF15<
Mechanical			
Stress at Break	ISO 527	MPa (kpsi)	110 (16.0)
Strain at Break	ISO 527	%	3.3
Tensile Modulus	ISO 527	MPa (kpsi)	6000 (870)
Unnotched Charpy Impact Strength	ISO 179/1eU	kJ/m ²	30
Thermal			
Deflection Temperature 1.80MPa	ISO 75-1/-2	°C (°F)	200 (392)
Melting Temperature 10°C/min	ISO 11357-1/-3	°C (°F)	224 (435)
Rheological			
Melt Volume-Flow Rate 250°C, 2.16kg	ISO 1133	cm ³ /10 min	26
Other			
Density	ISO 1183	kg/m ³ (g/cm ³)	1420 (1.42)
Molding Shrinkage	ISO 294-4	%	
Normal			1.1
Parallel			0.4

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc
ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
Test temperatures are 23°C unless otherwise stated.

The above data are preliminary and are subject to change as additional data are developed on subsequent lots.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Crastin® are trademarks or registered trademarks of DuPont Company. Copyright© 2008

080930/081008

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. CAUTION: Do not use DuPont materials in medical application involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-2 and DuPont CAUTION Regarding Medical Applications ... H-50102-2

Crastin® SK612SF NC010

Property	Test Method	Units	Value
Processing - Injection Molding			
Melt Temperature Range		°C (°F)	235-260 (465-500)
Melt Temperature Optimum		°C (°F)	240 (464)
Mold Temperature Range		°C (°F)	30-130 (85-265)
Mold Temperature Optimum		°C (°F)	80 (175)
Drying Time, Dehumidified Dryer		h	2-4
Drying Temperature		°C (°F)	110-130 (230-265)
Processing Moisture Content		%	<0.04

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm.
 Test temperatures are 23°C unless otherwise stated.

The above data are preliminary and are subject to change as additional data are developed on subsequent lots.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Crastin® are trademarks or registered trademarks of DuPont Company. Copyright© 2008

080930/081008

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. CAUTION: Do not use DuPont materials in medical application involving implantation in the human body or contact with internal body fluids or tissues unless the material has been provided from DuPont under a written contract that is consistent with DuPont policy regarding medical applications and expressly acknowledges the contemplated use. For further information, please contact your DuPont representative. You may also request a copy of DuPont POLICY Regarding Medical Applications H-50103-2 and DuPont CAUTION Regarding Medical Applications ... H-50102-2