

DuPont™ Zytel® HTN

high performance polyamide resin

PRELIMINARY DATA

Zytel® HTN54G35EF BK420

Zytel® HTN54G35EF BK420 is a 35% glass reinforced, toughened, heat stabilized, lubricated high performance polyamide resin, developed for electrical and electronics applications. It is also a PPA resin.

Property	Test Method	Units	Value
			DAM
Identification			
Part Marking Code	ISO 11469		>PA-IGF35<
Part Marking Code	SAE J1344		>PPA-IGF35<
Mechanical			
Stress at Break	ISO 527	MPa (kpsi)	185 (26.8)
Strain at Break	ISO 527	%	2.7
Tensile Modulus	ISO 527	MPa (kpsi)	10500 (1520)
Notched Charpy Impact Strength	ISO 179/1eA	kJ/m ²	11
Unnotched Charpy Impact Strength	ISO 179/1eU	kJ/m ²	82
Thermal			
Melting Temperature 10°C/min, First Heat	ISO 11357-1/-3	°C (°F)	300 (572)
Electrical			
Surface Resistivity	IEC 60093	ohm	1E+18
Volume Resistivity	IEC 60093	ohm m	1E+14

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.

ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm unless otherwise stated.

Test temperatures are 23°C unless otherwise stated.

During molding, use proper protective equipment and adequate ventilation. Avoid exposure to fumes and limit the hold up time and temperature of the resin in the machine. Purge degraded resin carefully with HDPE.

The above data are preliminary and are subject to change as additional data are developed on subsequent lots.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Zytel® are trademarks or registered trademarks of DuPont Company. Copyright© 2011

110330/110407

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. CAUTION: This product is not permitted to be sold for use in medical applications involving any implantation in the human body or where contact with internal body fluids or tissues will equal or exceed 24 hours. For applications involving contact of less than 24 hours, see "DuPont Medical Caution Statement", H-51012 and contact your DuPont sales representative.

Product Information

Zytel® HTN54G35EF BK420

Property	Test Method	Units	Value
			DAM
Other			
Density	ISO 1183	kg/m ³ (g/cm ³)	1420 (1.42)
Molding Shrinkage	ISO 294-4	%	
Normal			0.5
Parallel			0.2
Processing			
Melt Temperature Range		°C (°F)	320-330 (610-625)
Melt Temperature Optimum		°C (°F)	325 (620)
Mold Temperature Range		°C (°F)	85-135 (185-275)
Drying Time, Dehumidified Dryer		h	6-8
Drying Temperature		°C (°F)	100 (210)
Processing Moisture Content		%	<0.10

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc.
 ISO Mechanical properties measured at 4.0mm, ISO Electrical properties measured at 2.0mm, and all ASTM properties measured at 3.2mm unless otherwise stated.
 Test temperatures are 23°C unless otherwise stated.

The above data are preliminary and are subject to change as additional data are developed on subsequent lots.

The DuPont Oval Logo, DuPont™, The miracles of science™ and Zytel® are trademarks or registered trademarks of DuPont Company. Copyright© 2011

110330/110407

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials, additives or pigments or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. DuPont advises you to seek independent counsel for a freedom to practice opinion on the intended application or end-use of our products. CAUTION: This product is not permitted to be sold for use in medical applications involving any implantation in the human body or where contact with internal body fluids or tissues will equal or exceed 24 hours. For applications involving contact of less than 24 hours, see "DuPont Medical Caution Statement", H-50102 and contact your DuPont sales representative.