

DuPont™ Rynite® PET

thermoplastic polyester resin

Product guide and properties



1



2



3



4



Product guide and properties for RYNITE® PET

General description

RYNITE® is DuPont's registered trademark for its thermoplastic polyester resins based on polyethylene terephthalate (PET). They are specially formulated for rapid crystallisation during the injection moulding process and are reinforced with glass fibres or combinations of glass fibres with glass flake or mica. RYNITE® PET grades offer excellent dimensional stability, creep resistance, heat resistance, outstanding colour stability, high surface gloss and have inherent good electrical properties.

The properties of the standard grades are summarised in the following tables. Many more grades are available which are customised for special requirements (e.g. UL Encapsulation Systems) or technologies (e.g. gas injection, cold riveting etc.). RYNITE® PET is also available in colours as well as UV stabilized grades for exterior applications.

Applications

RYNITE® PET resins are used in numerous industry segments such as automotive, electrical and electronics, appliances, mechanical engineering etc. where they successfully replace metals and thermosets as well as other thermoplastic polymers. Some typical applications are windshield wiper arms, brake systems, motor end frames, microswitches, coil forms, lamp sockets, oven handles and iron skirts.

Processing

RYNITE® PET resins can be processed on standard injection moulding machines. They should be processed at melt temperatures of 280° to 290° C. Surface temperature of the mould should be at least 95° C. Some grades like 5211 S and 5213 S require a mould temperature of 120° C or above. Lower mould temperatures can lead to ejection problems, poor surface appearance and increased cycle times.

All grades of RYNITE® PET have to be dried to a moisture level below 0,02 % (4 hours at 120° C). The use of dehumidified driers is the only practical way to assure this. Too high a level of moisture during processing results in significant loss of toughness and strength. Unlike other polymers too high moisture levels in RYNITE® PET do not result in any visible surface defect. The "Moulding Manual for RYNITE®" (TRR 30) contains all relevant processing information and should be consulted before using the material.

Packaging

RYNITE® PET resins are supplied on pallets with 40 bags of 25 kg or in 1000 kg Octabin. Bulk shipment is also possible.

Safety information

DuPont supplies Material Safety Data Sheets (MSDS) information to its customers with the initial order and on the next order after an MSDS is revised. An MSDS includes such information as hazardous components, health hazards, emergency and first aid procedures, disposal procedures and storage information.

Environment

The good melt stability of RYNITE® PET normally enables the recycling of properly handled production waste. If recycling is not possible, DuPont recommends, as the preferred option, incineration with energy recovery. The incinerator has to be equipped with a state of the art scrubber in order to clean the flue gases before release.

RYNITE® PET is not soluble in water and has practically no additives which can be extracted by water. Therefore RYNITE® PET represents no known risk to human health or the environment when land filled. For disposal, local regulations have to be observed which can vary significantly from locality to locality.

Polyethylene terephthalate is mentioned on the 'green list' of the European Regulation EEC 259/93, Annex II. Thus, RYNITE® PET is not restricted for inter European transport of waste destined for recovery.

Cover pictures

- 1 – Connector
- 2 – Lamp socket
- 3 – Oven door frame and integrated control panel
- 4 – Rear windshield wipers

Compositions

Grade	Short description	Key properties	Major applications
Standard glass reinforced grades			
520	20 % glass fibre reinforced	Excellent melt flow characteristics. Offers a balance of strength, stiffness and toughness.	Housings
530	30 % glass fibre reinforced	Excellent melt flow characteristics. Outstanding balance of strength, stiffness and toughness, good electrical properties and excellent surface appearance. Close moulding tolerances, outstanding chemical and heat resistance.	Ignition components, coil caps, relay bases, sprockets, carburettor components, various pump housings, vacuum cleaner parts, window cranks, motor end frames.
536	36% glass fibre reinforced	Outstanding mechanical properties. High colour stability.	Body valves for servo break booster.
545	45 % glass fibre reinforced	Excellent melt flow characteristics. Superior strength and stiffness, with excellent dimensional stability and creep resistance, good electrical properties and surface appearance. Close moulding tolerances, outstanding chemical and heat resistance.	Motor end frame, compressor housings, fuel, air and temperature sensor housings, frames, coil bobbins, transmission components.
555	55 % glass fibre reinforced	Excellent melt flow characteristics. Excellent strength, dimensional stability, heat resistance and outstanding resistance to creep. Good electrical properties and surface appearance, excellent chemical resistance.	Clamps, structural housings and covers, transmission components, fixing parts for bumpers, coil encapsulations.
Flame retardant grades			
FR515	15 % glass fibre reinforced, flame retardant	Excellent balance of electrical and mechanical properties, good toughness and surface appearance. Very good high temperature resistance and high flow.	Electronic connectors, coil forms, switches, relays, lamp sockets, handles or frames.
FR530L	30 % glass fibre reinforced, flame retardant	Outstanding balance of strength, stiffness and toughness, good electrical properties and surface appearance. Close moulding tolerances, outstanding chemical and heat resistance.	Electrical/electronic connectors and high temperature bobbins used in applications employing vapour phase and wave soldering techniques.
FR543	43 % glass fibre reinforced, flame retardant	Outstanding balance of strength, stiffness and toughness, good electrical properties and surface appearance. Close moulding tolerances, outstanding chemical and heat resistance.	Electrical and electronic components such as connectors and coil forms.
FR943	43 % glass flake and glass fibre reinforced, flame retardant	Combination of very low warpage with outstanding balance of stiffness, strength, toughness, good surface appearance and electrical properties.	Electrical/electronic components such as connector bodies and terminal blocks requiring low warp characteristics.
Colour stable grades			
530CS	30% glass fibre reinforced	Outstanding colour stability at high temperatures compared to RYNITE® 530.	Housings and handles for domestic appliances.
936CS	36% glass flake and glass fibre reinforced	Combination of very low warpage with outstanding colour stability at high temperature.	Housings for domestic appliances and large parts, frames and handles.
Toughened			
415HP	15 % glass fibre reinforced, toughened	As a toughened resin provides excellent surface appearance in combination with increased elongation.	Electrical/electronic components, automotive and appliance housings.
408	30 % glass fibre reinforced, toughened	Improved impact resistance, excellent balance of strength, stiffness and temperature resistance.	Water pump housings, structural housings and brackets, handles.
Mineral and glass reinforced			
935	35 % mica/glass fibre reinforced	Low warpage and excellent dimensional stability over a wide temperature range. Good electrical properties.	Structural housings under the hood, electrical components.
940	40% glass fibre reinforced/mica	High strength and low warpage. Dimensional stability over a wide temperature range. Good electricals. Excellent adhesion to Epoxy potting resins.	Automotive ignition housings.

Properties of RYNITE® PET thermoplastic polyester resins

				Standard					
Property		Test method ISO	Units	520	530	545	555		
MECHANICAL	Stress at break ¹⁾	527-1/2	MPa	-40° C	148	218	242	221	
				23° C	120	158	182	196	
				93° C	58	83	92	96	
				150° C	41	55	67	71	
	Strain at break ¹⁾	527-1/2	%	-40° C	2,1	2,5	2	1	
				23° C	2,7	2,5	2	2	
				93° C	6	6	5	4	
				150° C	7	7	6	5	
	Tensile Modulus	527-1/2	MPa	7200	11000	15500	19500		
	Flexural Modulus	178	MPa	-40° C	7900	10300	15200	20700	
				23° C	6000	9000	13800	17900	
				93° C	2700	3600	5500	9200	
150° C				1800	2700	4000	5700		
Tensile Creep Modulus (1000 h)	23° C	899	MPa	5700	8800	13300	15300		
Charpy impact strength			kJ/m ²	23° C	9	11	11	11	
				-30° C	8	11	11	12	
				- unnotched	23° C	33	60	60	60
					-30° C	27	45	40	45
Izod impact strength		180	kJ/m ²	-30° C	7,7	10		16	
				23° C	9	10	11	15	
THERMAL	Melting temperature ²⁾	3146C	°C	252	252	252	252		
	Temperature of deflection under load ³⁾	75	°C	1,8 MPa	220	225	225	230	
				Vicat softening temperature	B/50	306	°C	228	228
	Coefficient of linear thermal expansion	11359-2	10 ⁻⁴ · K ⁻¹	parallel 23 to 55° C	0,25	0,1	0,13	0,08	
				normal	0,93	0,81	0,71	0,75	
	Temperature index:	(0,8 mm)	UL 746B	°C	Electrical	140	140	140	140
Mechanical w. impact					140	140	140	140	
Mechanical w/o impact					140	140	140	140	

1) Testing speed 5 mm/min.

2) Melting temperature determined by differential thermal analysis.

3) Deflection temperature under flexural load, annealed 30 minutes in oil at 50° C below melting point.

4) Flame-retarded resins are subject to specific UL processing and handling regulations for applications where an official UL rating is required. For more detailed information, please contact your Du Pont representative.

5) Numerical flame test ratings are not intended to represent behaviour of moulded parts in real life fire conditions; each enduser must determine whether any potential flammability hazards exist with parts moulded from RYNITE®. UL yellow card available upon request.

Flame retardant				Colour stable			Toughened		Mineral reinforced	
FR515	FR530L	FR543	FR943	536	530CS	936CS	415HP	408	935	940
138	193	217	156				145	206	121	
107	135	172	124	205	180	122	79	126	85	110
55	72	86	65				45	70	44	
38	45	52	43				36	55	30	
2,5	1,9	1,7	1,3				3	3	2	
2,6	2	1,8	1,5	2,5	2,5	2	5	3,3	2	2
4,7	3,5	4,3	4				14	7,0	5	
6,7	4	6,3	5,3				14,2	7,5	5	
6800	11500	17000	14000	14000	11000	11200	4700	9300	10200	12000
6500	11000	15100	14500				5900	8900	11800	
5900	9900	14500	13100				3600	8300	9600	
2400	4600	6900	5900				1300	3000	3400	
1500	2600	3100	3400				1100	2300	2200	
	9700								7700	
8	8,5	10	7	12	10,5	5,2	11	14	6	7
7	8,5	10	5				8	12	4	
40	40	43	30	65	50	25	55	70	25	35
35	33	30	25				25		20	
6	9,5						7,7		4	
6,7	8,0			11	9,5	3,8	12,5	12	5	6
252	252	252	250	250	245	247	252	250	252	250
200	220	225	220	225	225	210	205	220	200	225
210	218						206		204	
0,18	0,19	0,11				0,2	0,2		0,16	0,2
0,88	0,92	0,79				0,65	1,17		0,81	0,7
140	150	155	155				140	140	140	
140	150	155	155				120	140	140	
140	150	155	155				140	140	140	

All the above information is subject to the disclaimer printed on the back page of this document.

Properties of RYNITE® PET thermoplastic polyester resins

				Standard				
Property		Test method ISO	Units	520	530	545	555	
ELECTRICAL	Relative permittivity	10 ² Hz 10 ⁶ Hz	IEC 60250	–	4,2	4,2	4,5	4,8
					4,0	3,9	4,4	4,7
	Dissipation factor	10 ² Hz 10 ⁶ Hz	IEC 60250	10 ⁻⁴	300	130	70	70
					200	70	110	70
	Surface resistivity		IEC 60093	Ohm		10 ¹⁴	10 ¹⁴	
	Volume resistivity		IEC 60093	Ohm · m		10 ¹³	10 ¹³	
	Electric strength 1,0 mm disk	23° C	IEC 60243-1	kV/mm	33,5	35	32	35
	Comparative tracking Index (CTI)		UL 746A	PLC level	3	2	2	3
		IEC 60112	V	250	250	250	200	
Arc resistance		UL 746A	s		125	126	126	
FLAMMABILITY	Flammability ^{4), 5)} 0,8 mm		UL-94	–	HB	HB	HB	HB
	Glow wire	2 mm 3 mm	IEC 60695-2-1	°C	650	750	750	
					750	750	850	
Oxygen index		4589	%		20	20	22	
OTHERS	Density		1183	g/cm ³	1,46	1,56	1,69	1,80
	Humidity absorption, 50% RH, 23° C Water absorption, saturation, 23° C		62	%	0,2	0,2	0,14	0,11
					1,0	0,78	0,62	0,59
	Hardness Rockwell scale M scale R		2039/2	–	90	100	100	100
					120	120	120	120
	Coefficient of friction against self against steel		ASTM D 1894	–		0,18	0,17	0,27
					0,17	0,20	0,18	
Taber abrasion CS-17 wheel, 1000 g		ASTM D 1044	mg/1000 cycles		30	44		
PROCESSING	Mould shrinkage, plates 60 × 60 × 2 mm parallel normal	294-4	%	0,25	0,20	0,25	0,25	
				0,85	0,80	0,85	0,80	

1) Testing speed 5 mm/min.

2) Melting temperature determined by differential thermal analysis.

3) Deflection temperature under flexural load, annealed 30 minutes in oil at 50° C below melting point.

4) Flame-retarded resins are subject to specific UL processing and handling regulations for applications where an official UL rating is required. For more detailed information, please contact your Du Pont representative.

5) Numerical flame test ratings are not intended to represent behaviour of moulded parts in real life fire conditions; each enduser must determine whether any potential flammability hazards exist with parts moulded from RYNITE®. UL yellow card available upon request.

All the above information is subject to the disclaimer printed on the back page of this document.

All the above information is subject to the disclaimer printed on the back page of this document.

Flame retardant				Colour stable			Toughened		Mineral reinforced	
FR515	FR530L	FR543	FR943	536	530CS	936CS	415HP	408	935	940
3,7	4,8								4,5	3,8
3,7	4,7	4,1	4,1					3,3	4,1	3,7
90	70								300	70
150	100	170	150					150	250	150
10 ¹³	10 ¹⁴	10 ¹⁵	10 ¹⁵				10 ¹³	10 ¹⁴	10 ¹⁴	10 ¹⁴
10 ¹³	10 ¹³	10 ¹³	10 ¹⁵				10 ¹¹	10 ¹⁵	10 ¹³	10 ¹⁵
34	33								39	
3	2	3	2				2	2	2	
225	250	250	225		250	250			300	
67	117	124	102				95		131	
V-0	V-0 at 0,35 mm	V-0 at 0,35 mm	V-0				HB	HB	HB	HB
	960 (at 1,2 mm) 960									
32	33	35	31		22		19	22		
1,53	1,67	1,79	1,78	1,64	1,59	1,63	1,39	1,49	1,58	1,64
	0,17 0,77	0,11 0,62	0,1 1,0		0,16 0,6		0,25 2,5		0,13 0,83	
88	100	102	91				58	70	75	75
120	120	122	116				111	115	115	115
0,21	0,18	0,18	0,29				0,42		0,21	
0,18	0,19	0,16	0,18				0,27		0,19	
88	38	69	82				35			81
0,35	0,25	0,20	0,25	0,25	0,15	0,20	0,35	0,25	0,30	0,20
0,85	0,90	0,75	0,65	0,80	0,60	0,40	0,85	0,85	0,70	0,70

* PLC levelL CTI
0 TI ≥ 600
1 600 ≥ TI ≥ 400
2 400 ≥ TI ≥ 250
3 250 ≥ TI ≥ 175
4 175 ≥ TI ≥ 100
5 100 ≥ TI ≥ 0

All the above information is subject to the disclaimer printed on the back page of this document.

For further information on Engineering Polymers contact:

Internet location: <http://plastics.dupont.com>

Belgique / België

Du Pont de Nemours (Belgium)
Antoon Spinostraat 6
B-2800 Mechelen
Tel. (15) 44 14 11
Telex 22 554
Telefax (15) 44 14 09

Bulgaria

Serviced by Biesterfeld Interowa GmbH & Co. KG.
See under Österreich.

Česká Republika a Slovenská Republika

Du Pont CZ, s.r.o.
Pekarska 14/268
CZ-155 00 Praha 5 – Jinonice
Tel. (2) 57 41 41 11
Telefax (2) 57 41 41 50-51

Danmark

Du Pont Danmark A/S
Skjøtevej 26
P.O. Box 3000
DK-2770 Kastrup
Tel. 32 47 98 00
Telefax 32 47 98 05

Deutschland

Du Pont de Nemours
(Deutschland) GmbH
DuPont Straße 1
D-61343 Bad Homburg
Tel. (06172) 87 0
Telex 410 676 DPD D
Telefax (06172) 87 27 01

Egypt

Du Pont Products S.A.
Bldg no. 6, Land #7, Block 1
New Maadi
ET-Cairo
Tel. (00202) 754 65 80
Telefax (00202) 516 87 81

España

Du Pont Ibérica S.A.
Edificio L'IIlla
Avda. Diagonal 561
E-08029 Barcelona
Tel. (3) 227 60 00
Telefax (3) 227 62 00

France

Du Pont de Nemours (France) S.A.
137, rue de l'Université
F-75334 Paris Cedex 07
Tel. 01 45 50 65 50
Telex 206 772 dupon
Telefax 01 47 53 09 67

Hellas

Ravago Plastics Hellas ABEE
8, Zakythou Str.
GR-15232 Halandri
Tel. (01) 681 93 60
Telefax (01) 681 06 36

Israël

Gadot
Chemical Terminals (1985) Ltd.
22, Shalom Aleichem Street
IL-633 43 Tel Aviv
Tel. (3) 528 62 62
Telex 33 744 GADOT IL
Telefax (3) 528 21 17

Italia

Du Pont de Nemours Italiana S.r.L.
Via Volta, 16
I-20093 Cologno Monzese
Tel. (02) 25 30 21
Telefax (02) 25 30 23 06

Magyarország

Serviced by Biesterfeld Interowa GmbH & Co. KG.
See under Österreich.

Maroc

Deborel Maroc S.A.
40, boulevard d'Anfa – 10°
MA-Casablanca
Tel. (2) 27 48 75
Telefax (2) 26 54 34

Norge

Distrupol Nordic
Niels Leuchsvei 99
N-1343 Eiksmarka
Tel. 67 16 69 10
Telefax 67 14 02 20

Österreich

Biesterfeld Interowa GmbH & Co. KG
Bräuhausgasse 3-5
P.O. Box 19
AT-1051 Wien
Tel. (01) 512 35 71-0
Fax (01) 512 35 71-31
e-mail: info@interowa.at
internet: www.interowa.at

Polska

Du Pont Poland Sp. z o.o.
ul. Prosta 69
PL-00-838 Warszawa
Tel. (022) 691 09 01
Telefax (022) 691 09 10

Portugal

ACENYL
Rua do Campo Alegre, 672 – 1°
P-4100 Porto
Tel. (2) 69 24 25/69 26 64
Telex 23 136 MACOL
Telefax (2) 600 02 07

Romania

Serviced by Biesterfeld Interowa GmbH & Co. KG.
See under Österreich.

Russia

E.I. du Pont de Nemours & Co. Inc.
Representative Office
B. Palashevsky Pereulok 13/2
SU-103 104 Moskva
Tel. (095) 797 22 00
Telex 413 778 DUMOS SU
Telefax (095) 797 22 01

Schweiz / Suisse / Svizzera

Dolder AG
Immengasse 9
Postfach 14695
CH-4004 Basel
Tel. (061) 326 66 00
Telefax (061) 322 47 81
Internet: www.dolder.com

Slovenija

Serviced by Biesterfeld Interowa GmbH & Co. KG.
See under Österreich.

Suomi / Finland

Du Pont Suomi Oy
Box 62
FIN-02131 Espoo
Tel. (9) 72 56 61 00
Telefax (9) 72 56 61 66

Sverige

Du Pont Sverige AB
Box 23
SE-164 93 Kista (Stockholm)
Tel. (8) 750 40 20
Telefax (8) 750 97 97

Türkiye

Du Pont Products S.A.
Turkish Branch Office
Sakir Kesebir cad. Plaza 4
No 36/7, Balmumcu
TR-80700 Istanbul
Tel. (212) 275 33 82
Telex 26541 DPIS TR
Telefax (212) 211 66 38

Ukraine

Du Pont de Nemours
International S.A.
Representative Office
3, Glazunova Street
Kyiv 252042
Tel. (044) 294 96 33/269 13 02
Telefax (044) 269 11 81

United Kingdom

Du Pont (U.K.) Limited
Maylands Avenue
GB-Hemel Hempstead
Herts. HP2 7DP
Tel. (01442) 34 65 00
Telefax (01442) 24 94 63

Argentina

Du Pont Argentina S.A.
Avda. Mitre y Calle 5
(1884) Berazategui-Bs.As.
Tel. +54-11-4229-3468
Telefax +54-11-4229-3117

Brasil

Du Pont do Brasil S.A.
Al. Itapecuru, 506 Alphaville
06454-080 Barueri-São Paulo
Tel. (5511) 7266 8229

Asia Pacific

Du Pont Kabushiki Kaisha
Arco Tower
8-1, Shimomeguro 1-chome
Meguro-ku, Tokyo 153-0064
Tel. (03) 5434-6935
Telefax (03) 5434-6965

South Africa

Plastamid (Pty) Ltd.
43 Coleman Street
P.O. Box 59
Elsies River 7480
Cape Town
Tel. (21) 592 12 00
Telefax (21) 592 14 09

USA

DuPont Engineering Polymers
Barley Mill Plaza, Building #22
P.O. Box 80022
Wilmington, Delaware 19880
Tel. (302) 999 45 92
Telefax (302) 892 07 37

Requests for further information from countries not listed above should be sent to:

Du Pont de Nemours International S.A.

2, chemin du Pavillon
CH-1218 Le Grand-
Saconnex/Geneva
Tel. (022) 717 51 11
Telex 415 777 DUP CH
Telefax (022) 717 52 00

The information provided in this documentation corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits nor used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since DuPont cannot anticipate all variations in actual end-use conditions DuPont makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.

Caution: Do not use this product in medical applications involving permanent implantation in the human body. For other medical applications see "DuPont Medical Caution Statement".



The miracles of science™